



**THERMAGRUNT-AM**  
SILICONE PRIMER



Compilation date: 2016-10-03

### APPLICATION/CHARACTERISTICS:

THERMAGRunt-SN silicone primer is intended for preparing the substrate under THERMATynk-SN thin-layered silicone top coat. It can be used on all even and mineral substrate such as concrete, gypsum, traditional cement or cement-lime, plasters plasterboards and others. It can be used both for internal and external applications.

### SUBSTRATE PREPARATION:

The substrate should be stable, even and adequately strong, without any layers that could reduce adhesion, in particular dust, dirt, lime, oils, grease and wax. Remove old paints and plasters with unsatisfactory adhesion. Level off and infill any irregularities in substrate or cavities.

### PREPARATION:

THERMAGRunt-SN primer is supplied as a ready to use product. It cannot be mixed with other materials, diluted or thickened. After opening the bucket, its content must be stirred thoroughly to obtain homogenous consistency. Apply the THERMAGRunt-SN primer on to prepared in advance (evenly across the entire surface) substrate using a roller or brush. Do not apply the primer at the temperature below +5 °C. You can render the surface after the mix dries off completely, i.e. after about 5-6 hours of the application.

### COVERAGE:

About 0.2 L per 1 sq. m.

### NOTE:

Protect eyes and skin. Seek medical advice in case of direct contact with eyes.

### STORAGE AND TRANSPORT:

Transport and store in a tightly sealed original containers (preferably on pallets), in dry conditions at the temperatures above zero. Protect against frost and overheating. Do not leave open containers.

### SHELF LIFE:

12 months from the manufacture date stated on the container.

**MANUFACTURING DATE/COLOUR:** stated on the container.

### PACKAGING:

5 L bucket; 72 buckets per pallet, 360 L;  
10 L bucket; 44 buckets per pallet, 440 L.

### TECHNICAL PARAMETERS

Ingredients	water dispersion, synthetic resins and mineral fillers
Colour	white or colour
Density	about 1,4 kg/dm <sup>3</sup>
Application temperature	od +5°C do +25°C
Drying time	about 4 hrs
Consumption	About 0.2 L/m <sup>2</sup> depending on the substrate absorption
Technical specification	ETA 15/0311 dated 29/05/2015