



## SILICATE-SILICONE PRIMER



2016-07-04

### APPLICATION/CHARACTERISTICS:

DLX P-60 is a primer used to prepare the substrate under DLX T-60 thin-layered silicate-silicone top coats. It can be used on all even mineral substrates capable of holding the paint, such as concrete, traditional cement or cement-lime plasters and others. It can be used both for internal and external applications.

### SUBSTRATE PREPARATION:

The substrate should be stable, even and adequately strong, without any layers that could reduce adhesion, in particular dust, dirt, lime, oil, grease and wax. Remove old paints and plasters with unsatisfactory adhesion. Level off and remove any rough places and cavities.

### PREPARATION:

The DLX P-60 primer is supplied as a ready to use product. It cannot be mixed with other materials, diluted or thickened. After opening the bucket, its content must be stirred thoroughly to obtain homogenous consistency. Apply DLX P-60 on the substrate prepared in advance (evenly across the entire surface) using a roller or brush. Do not apply the mix at a temperature below +5°C. You can render the surface after the mix dries off completely, i.e. after about 4-6 hours from application.

### COVERAGE:

About 0.2 L per 1 m<sup>2</sup>.

### NOTE:

Protect eyes and skin. Seek medical advice in case of direct contact with eyes.

### STORAGE AND TRANSPORT:

Transport and store in tightly sealed original packaging (preferably on pallets), in dry conditions at temperature over zero degrees. Protect against frost and overheating. Do not leave open containers.

### SHELF LIFE:

12 months from the manufacture date stated on the container.

### PACKAGING:

5 L bucket; 72 buckets per pallet, 360 L;  
10 L bucket; 44 buckets per pallet, 440 L.

### TECHNICAL PARAMETERS:

Ingredients	Liquid potassium glass, silicone resin water dispersion, quartz aggregate
Colour	white or colour
Density	about 1.4 kg/dm <sup>3</sup>
Application temperature	+5°C to +25°C
Drying time	about 4 hrs
Consumption	About 0.2 L/m <sup>2</sup> depending on the substrate absorption
Technical specification	ETA 15/0311 dated 29/05/2015

THIS PRODUCT IS THE PART OF

